

"Rizogard" TM -2250"

Prime coating
TU 2316-XXX-43548961-2010

Description	Mono component low viscosity compound based on water dispersion of sterol acrylic
Application	Ready for using polymer dispersion based on water intended for manufacture of a primer mixes of " Rizotop ™ -2210»; « Rizotop ™ -2220»; « Rizotop ™ -2250 "and as a binder composition to the dry mixture " Rizotop ™ -2250 ».
Advantages	<ul style="list-style-type: none"> - It is well absorbed and penetrates into the concrete. - Strengthens the foundation. - Fast cure. - Economical (low consumption).
Certificates	- Sanitary-Epidemiological Conclusion of the Federal Service for Supervision of Consumer Rights Protection and Human Welfare 77.99.34.225.D.011360.09.07 number of 26.09.2007.
Application systems	<p>As a primer for the "Rizotop™ -2220» "Rizogard™ - 2250" + 200% water, - 0,10 ÷ 0,20 * kg / sq.m. * - the consumption is shown with the addition of water, depending on the absorbency of the ground.</p> <p>As a primer for the "Rizotop™ -2210» and «Rizotop™ -2250» "Rizogard™ - 2250" + Water + ПЦ-500 (1:2:4-5 ***) - 0,50 ÷ 0,70 kg / m. ** ** - Primer using on the technology "fresh on fresh" *** - Depending on using PC</p> <p>As sealer in the manufacture of polymer modified coatings A dry mix "Rizotop™ -2250» (90 kg). closes 6.8 kg. "Rizogard™ - 2250."</p>
Restrictions	<ul style="list-style-type: none"> - There should not be still water, drops of dew on the surface,; - Maximum relative humidity is 85%; - Protection from rain and water leaks within 24 hours; - Minimum substrate temperature during coating is + 5 ° C. - The maximum substrate temperature during coating is +30 ° C
Surface preparation	Surface must be clean and free of still water, drops of dew. Contaminations of surfaces such as sand, dirt, oil, grease, rubber residues, etc. is removed mechanically with a scraper or brush.
Mixing	<p>As a primer: Before the application shake can "Rizogard™ - 2250" 3-4 times well to mix the contents. Pour into a suitable container the amount needed for the application, add estimated number of water and / or cement, mixed with slow-speed mixer to form a homogeneous mixture (without lumps), the remainder close in a tightly original package.</p> <p>As sealer: Before the application shake can "Rizogard™ - 2250" 3-4 times well to mix the contents. Pour into a suitable container quantity for mixing the dry mixture "Rizotop™ -2250.</p>
Applying	To obtain a uniform layer of " Rizogard ™ - 2250" apply with a roller. Compound " Rizotop ™ -2210» and « Rizotop ™ -2250» using the technology "fresh on fresh" Recommended area for working division is primed, defined by speed of stacking of main layers " Rizotop ™ -2210» and « Rizotop ™ -2250». Not prevent drying of the primer.

Technical data

Packages	Can	20kg
	Physical data	
Density (State Standard 28513-90) at +20C	1.01±0.1g/cm3	
Contents of nonvolatile substance (State Standard	Not more 18%	

12.1.014-84*)	
Reaction capability	Drying time till 3 level, at 20±2C temperature, not more -6 (State Standard 19007-73)
Storage	It is allowed freezing during transport. Store in a dry, heated conditions at temperatures between +5 ° C to +30 ° C. It is avoid direct exposure to solar rays, heat and moisture.
Warranty period	12 months from the date of registration under recommended storage conditions in original packaging.
Safety precautions	You must use protective clothing, gloves and spectacles. In case if compound enters the eyes, respiratory system or skin, wash immediately with warm water, if necessary, consult a doctor. "Rizogard™ - 2250" can contaminate water sources in the liquid state, it cannot be discharged into sewage drains and ponds, as well as inadmissible its penetration into the soil.
Clearance	At the end of work the tool must be cleaned with water. Wash hands and exposed skin with soap and water.

The information contained herein is based on a generalized technical and practical experience. Due to the inability to control the conditions of application of the material, affecting the process, Producer does not accept legal and other responsibility rising for the misuse or interpretation of this information. Specifications of material and equipment provided here are subject to change without prior notice.

For complaints, suggestions and complaints please contact: proposal@cmt-product.ru.