

«Rizokon™»

Textural Mosaic Elastic Covering (3.0-4.0 mm)

Application: It is used for industrial and decorative flooring which withstands high mechanical effect of rubber and plastic wheeled transport and small carts and chemical influence of water and combustible and lubricating materials, acids and alkali of high intensity.

Basement leveling

№	Usage	Material	Consumption on kg/m ²		Tools Mode
1.	Primer	Rizopox™ – 1100 / Rizopur - 1700	0.3 ÷ 0.4		A solvent resistant roller, Pile height is 12 – 18 mm
	Powdering (if necessary)	Ignite quartz sand, fraction 0.1 ÷ 0.4 mm	0.3 ÷ 0.4		By hand
2.	Basic layer	Rizopur™ – 4120	1.4 ÷ 1.6		Metal trowel or a serrated spatula
	Filling up	Ignite quartz granules Fraction 3.0-8.0	6.0 ÷ 7.0		By hand to the state of pick dressing
3.	Cleaning of surface				Remove excess granules. Clean the surface by a grinding machine with corundum elements to even a surface (grind only roughness) Dedust the surface by a vacuum cleaner
4.	Pores filling layer ¹	Rizopur™ - 4120	1.0 ÷ 1.2		Use a stopping knife (strip mode)

Total thickness: 3.0 – 4.0 mm

Recommendation:

1. The quality of grinding influences on the evenness of a surface
2. Basic requirements are given in the material description
3. It is necessary to treat the surface by a spiked roller after laying Rizopur™-4120
4. Use grinding 2 days after laying Rizopur™ – 4120 with granules filling up.

When choosing flooring it is necessary to take into account all data. Address your requests to the Manufacturer.